

Pengutex TC

Technical Data Sheet



Product description

Penguin Pengutex TC is an acrylic copolymer based component that gives ornaments to the wall. It is intended for ornament systems which are formed by special layers. Penguin Universal Primer must be applied on harrowed surface, then Penguin Pengutex TC has to be sprayed as a second layer with airless spray and can be given ornaments with crushing method at this stage. After this stage, Penguin Penakril Primer must be applied one layer and two layer of top layer paint which is for exterior must be applied at last.

Sphere of usage

Penguin Pengutex TC can be used on the surfaces like exterior wall, priming, plaster, concrete, plasterboard and betopan. The temperature of surface must be between +5°C and +30°C during application and humidity can be maximum 80%. It can be thinned with maximum 10% water.

Physical specifications

Color	Multicolor
Dry residue content (weight %)	85±2%
Density (gr/cm³)	1.8±0.02 q/ml
Brightness	Mat

Surface preparation

Before application, the surface must be cleaned of old paint residues, dust, dirt and oil residues. Penguin Before Pengutex TC coating, Penguin Universal Primer is applied to the surface. With an airless gun as a second layer Penguin Pengutex TC is sprayed, crush patterned and top coated for outdoor use paint is applied in two layers. Surface temperature should be between +5-+30°C, relative humidity should not exceed 80%. The product can be diluted with water up to 10%.

Application methods

Spray	Airless spray or convention spray can be used
Brush	Appreciate
Roller	Appreciate

Drying duration

The drying time mainly depends on the weather conditions, the thickness of the applied layer and the number of applied layers. Approximate drying time depending on the air temperature of the paint in the table belowshown

- - The area to be painted should be well ventilated (Open air or free air circulation)
- - The paint should be applied at the recommended thickness
- - Relative humidity should not be above 80%

Air temperature	10°C	23°C
Upper drying	5 hour	1 hour
Complete (hard) drying	20 hour	8-10 hour

"CMT Group" MMC

Ünvan: Badamdar shos. 27, Bakı, Azərbaycan
Tel: (+994 12) 502 45 50
E-mail: office@cmt.com.az
Web-site: www.penguin.az



Pengutex TC

Technical Data Sheet



Storage conditions

Paint in dry, cool, well-ventilated warehouses without direct sunlight, between +5°C and +35°C should be kept uncapped. It should be mixed well before use. Shelf life 3 years in unopened packaging.

Packing types

It is produced in 25 kg plastic containers.

The implementing operator

This product is intended for professional use. Applicator or operator experienced and product should be aware of. The person in question should mix the paint according to the application and apply should do. Employees participating in the application must be provided with safety equipment.

Product color

It can be painted in any color with water-based pastes. Small in the color of the product from batch to batch differences may exist.

Attention

The above information is based on results obtained in laboratory tests and field applications prepared. In applications outside the company's control, the company is solely responsible for the quality of the paint is responsible. It is not responsible for problems that may arise from implementation and application errors.

Health and safety rules

Follow the rules on the containers. Store in depots where there is not any risk for high temperature and sparks. Use in good-ventilated places. If there is a contact with paint, first clean it with proper solvent and then wash skin with water and soap. If eyes contact with paint, it must be cleaned water and doctor intervention is important.

Note: "CMT GROUP" LLC keeps the right to change information provided above without any notification.

"CMT Group" MMC

Ünvan: Badamdar shos. 27, Bakı, Azərbaycan

Tel: (+994 12) 502 45 50

E-mail: office@cmt.com.az

Web-site: www.penguin.az



Web-site: www.penguin.az